

CLAIMS

1. A transparent elastomer composition comprising an elastomer and fluorine-containing resin fine particles which are finely dispersed in the elastomer.

2. A composition comprising a transparent elastomer composition which comprises an elastomer and fluorine-containing resin fine particles which are finely dispersed in the elastomer and further containing a filler.

3. The composition of Claim 1 or 2, wherein the elastomer is a fluorine-containing elastomer.

4. The composition of any of Claims 1 to 3, wherein the composition contains a crosslinking agent.

5. The composition of any of Claims 1 to 4, wherein the transparent elastomer composition has a haze value of not more than 50 %.

6. A process for preparing the transparent elastomer composition of Claim 1, which comprises mixing an emulsion of elastomer particles and an emulsion of fluorine-containing resin fine particles, and co-coagulating the mixture.

7. The process of Claim 6, wherein the emulsion of fluorine-containing resin fine particles is an emulsion of fluorine-containing resin fine particles having an average particle size of from 20 to 150 nm.

5

~~Sw 27
A21~~ 8. An elastomeric molded article which is obtained by vulcanizing and molding the composition of any of Claims 1 to 5.

9. The elastomeric molded article of Claim 8, which is transparent.

10

10. The elastomeric molded article of Claim 9, which has a haze value of not more than 50 %.

~~Held
A21~~